



ARDEX AF 130

Project adhesive resilient coverings

- Good initial adhesion
- Very low emissions

ARDEX system product: Particularly secure bonding properties with ARDEX levelling compounds designed for odourless behaviour and clean indoor air.



Area of application

Indoor. Floor.

Dispersion adhesive for bonding:

- LVT flooring
- CV coverings
- PVC design flooring (LVT)

on absorbent substrates.

Art

Composition: polymer dispersions, modified natural resins, mineral fillers, water, wetting agents, thickening agents, defoamers and preservatives.

Preparation of the surface

The substrate must comply with the requirements of ÖNORM B 5236 Planning and execution of floor covering and wooden flooring work. In particular, it must be level, permanently dry, solid, load-bearing, free of release agents and cracks, and resistant to tension and pressure, or it must be prepared accordingly.

Filling work is carried out using suitable ARDEX levelling compounds in combination with ARDEX primers.

Processing

The coverings to be bonded must be acclimatised and free of tension. ARDEX AF 130 Object Adhesive for Elastic Coverings is applied evenly to the appropriately prepared substrate using a notched trowel. Avoid pockets of adhesive. The airing time depends on the room climate, substrate and material temperature, absorbency of the substrate and the notched trowel used, and can be up to approx. 10 minutes.

Low temperatures and higher relative humidity prolong the times and can lead to moisture entrapment. The times specified refer to +18°C and 65% relative humidity.

When laying PVC/CV flooring in particular, do not apply more adhesive than can be laid during the wet phase of the adhesive. The adhesive must still be easily wettable and easily compressible. Check repeatedly that the flooring is wet. Lay the flooring without air pockets, avoiding seam compression, rub immediately and weigh down if necessary.

After approx. 20 minutes, roll with a multi-section roller (min. 50 kg).

Recommended notched trowel and application quantity

The notched trowel must be selected to ensure that the back of the coating is sufficiently wetted. Coarse-textured coating backs or coarse-pored substrate surfaces require a suitable notched trowel.



TKB A1

Application: 280 - 320 g/m² *

TKB A2

Application: approx. 330 g/m² *

ARDEX Baustoff GmbH
Hürmer Straße 40
A-3382 Loosdorf
AUSTRIA
+43 (0) 2754/7021-0
+43 (0) 2754/2490
office@ardex.at
www.ardex.at

Manufacturer with certified
QM/UM system according to
EN ISO 9001/14001

ARDEX AF 130

Project adhesive resilient coverings

*) Application quantities determined using Pajarito notched trowels on ARDEX levelling compounds.

Practical tip

Seal joints in the flooring after 24 hours at the earliest.

In case of doubt, carry out test bonding.

Observe the laying instructions of the covering manufacturer and the applicable standards and rules of the trade!

Remove any skin on the adhesive (e.g. due to improper storage or after opening) and do not stir it in.

Note

The information in our safety data sheets must be observed.

For commercial users only!

Additional information

Proceed carefully during application: avoid dust formation and release into the environment.

Dispose of the container and its contents in a sealed state in accordance with applicable local/regional/national/international regulations.

Waste disposal

Dispose of the container and its contents in a sealed state in accordance with applicable local/regional/national/international regulations.

Technical data according to ARDEX quality standard

Material requirements	280 - 330 G/m ² depending on the notched trowel used
Base	Special plastic dispersion
Flash-off time approx.	0 - 10 Minutes
Processing temperature	+15 °C
Insertion time approx.	10 - 20 Minutes
Relative humidity (RH)	75 % (max.)
Cleaning agents	Before drying: water

Product details

Suitable for underfloor heating	Yes
Chair castor suitability	Yes (rolls according to ÖNORM EN 12529)
Suitable for shampooing and spray extraction	Yes
Labelling according to GHS/CLP	See relevant safety data sheet
Labelling according to ADR	See relevant safety data sheet
EMICODE	EC 1 PLUS = very low emissions PLUS
GISCODE	D1 = Solvent-free dispersion installation materials
Blue Angel	DE-UZ 113
Packaging	Bucket with 13 kg net
Storage	Can be stored in a cool but frost-free place for approx. 12 months in the original sealed container. Store in dry rooms. Seal opened containers tightly.